

FACTICE TECHNICAL DATA SHEET

GRADE: BROWN RG 50

Typical Properties of Material	
Free Sulphur %	0.8 max
Petroleum Ether Extract %	Not Applicable
Acetone Extract %	29.0 +/- 3.0
Ash Content %	0.5 max
Specific Gravity	1.05 +/- 0.05
Appearance	Dark Brown Granules

Application:

- Open cured profiles and hoses
- Bicycle valve tubings
- Printing rollers
- Fabric proofing

Advantages:

- It improves the process of extrusion and decreases TC 90 i.e. curing time.
- It gives solvent as well as swelling resistance

Storage Recommendation:

Material must be stored away from the heat in dry and cool area, direct sunlight to be avoided.

Packing:

Standard packing for this grade is 30 Kgs per bag. HDPE bag with LDPE liner inside.