



## FACTICE TECHNICAL DATA SHEET

### GRADE: SOFTICE G

Typical Properties of Material	
Free Sulphur %	0.8 max
Petroleum Ether Extract %	40.0 +/- 3.0
Acetone Extract %	Not Applicable
Ash Content %	0.5 max
Specific Gravity	1.05 +/- 0.05
Appearance	Dark Brown Soft Lumps

### Application:

- Printing rollers
- Soft articles
- Bicycle tubes
- Compatible to natural and other synthetic polymers

### Advantages:

- It reduces the hardness of the compound to a great extent and maintains the softness permanently.
- It can substitute the plasticizers like DOP up to 75%.
- It helps to achieve very low shore hardness.
- Its use in Hypalon maintains original softness of articles permanently.

### Storage Recommendation:

Material must be stored away from the heat in dry and cool area, direct sunlight to be avoided.

### Packing:

Standard packing for this grade is 50 Kgs per bag. HDPE bag with LDPE liner inside.